

TEST REPORT

APPLICANT : Dragonshine Co.,Ltd

ADDRESS : A302 Meidu Plaza ,Moganshan Rd,310011, Hangzhou,
P.R.China

SAMPLE DESCRIPTION : Texlyweave& Texlymat

FIBER CONTENT : 70% PVC, 30% PET

END USE : Pavage


SAMPLE RECEIVED DATE : 27-Aug-2012

TURN AROUND TIME : 27-Aug-2012 To 30-Aug-2012, 4 Working Days

TEST REQUESTED	RESULT
- Phthalates Content	Pass


Eurofins (Shanghai) contact informationCustomer service: CarolZhang@eurofins.com / 021- 61819163 / 18221711029Sales specialist: DannyDai@eurofins.com / 021-61819175 / 13671918921

***** FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *****

Signed for and on behalf of
Eurofins Product Testing Service (Shanghai) Co., Ltd

Chris Zhang
Lab Manager

SAMPLE PHOTO



EFSH12081186-ST

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test method : Refer to US EPA 3540C:1996 and US EPA 8270D:2007. Solvent extraction and quantification by gas chromatography-mass selective detector (GC-MS)

Requirement : Regulation (EC) No 552/2009 amending Annex XVII of REACH Regulation (EC) No 1907/2006 (previously restricted under Directive 2005/84/EC)

Parameters	CAS No.	Unit	Requirement	Test Result			Conclusion
				1	2+3	4+5	
Dibutylphthalate (DBP)	84-74-2	%	--	n.d.	n.d.	n.d.	--
Benzylbutylphthalate (BBP)	85-68-7	%	--	n.d.	n.d.	n.d.	--
Diethylhexylphthalate (DEHP)	117-81-7	%	--	n.d.	n.d.	n.d.	--
Sum (DBP + BBP + DEHP)	--	%	0.1	n.d.	n.d.	n.d.	Pass
Di-n-octyl phthalate (DNOP)	117-84-0	%	--	n.d.	n.d.	n.d.	--
Di-iso-nonyl phthalate (DINP)	28553-12-0	%	--	n.d.	n.d.	n.d.	--
Di-iso-decyl phthalate (DIDP)	26761-40-0	%	--	n.d.	n.d.	n.d.	--
Sum (DNOP + DINP + DIDP)	--	%	0.1	n.d.	n.d.	n.d.	Pass

Component No.	Component
1	Black leatherette
2	Black strip
3	Grey strip
4	White strip
5	Blue strip

Note:

- n.d. = not detected, less than method detection limit 0.005%

Remark: According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

*** END OF THE REPORT ***